

Dr. Fixit Pidicrete WP



HEAVY DUTY, HIGH SOLID CONTENT (47%), ACRYLIC WATERPROOFING COATING

Description

Dr. Fixit Pidicrete WP is a high solid content (47%) acrylic co-polymer liquid, which when mixed with cement, forms a matrix & hence provides excellent waterproofing properties. It can also be used as a bonding agent for new to old cementitious substrates & as an additive for repair mortars.

Standard Compliance

Meets the requirements of BS 6319 Part 4:1984, BS 7542:1992, BS 6319 Part 2: 1983

Areas of Application

Waterproofing of concrete and sand-cement mortar used in

- Waterproofing - Additive with cement for waterproofing of roofs, walls & water storage tanks.
- Concrete repair - Additive for cement: mortar for repairs to spalled concrete, floor, columns, beams, chajja, slab etc
- Bond coat - Bond coat for old to new concrete & masonry plaster
- Priming - Reinforcement steel.

Features & Benefits

- Waterproofing - Improves waterproofing properties when used as a coating mixed with cement
- Chloride-free - Contains no chloride hence lesser chances of chloride contamination
- Bonding - Provides excellent bond to concrete & masonry plaster
- Strength - Improves tensile, flexural and compressive strength as compared to control concrete hence increases the durability of structures.

Method of Application

Waterproofing

1. Surface preparation

- Clean the surface with wire brush or scrubber to remove hidden dirt, loose particles, laitance & dust. Degrease the surface by using suitable solvents.
- Repair the spalled concrete portion by saw, cutting the extreme edges of the repair location to a depth of at least 10 mm to avoid featheredging & to provide strong bond.
- Clean the concrete surface to remove any contamination where breaking is not possible. Roughen the surface by light scabbling or grit blasting.
- For priming of concrete substrate, the surface should be thoroughly saturated with potable water. Remove any excess of water prior to application.

As a Waterproofing Coating

- For a waterproofing coating Mix Dr. Fixit Pidicrete WP: Cement in the ratio 1:1 by volume
- Mix for 2-3 minutes to avoid air entrapment. Keep on slowly adding cement to Dr. Fixit Pidicrete WP until the required consistency is achieved
- Brush apply 2coats of the mix in a span of 4-6 hours on the prepared concrete substrate
- Overlay the coating with a protective screed to the desired slope & thickness

CCDFRPPDWP0911A

Dr. Fixit Pidicrete WP

HEAVY DUTY, HIGH SOLID CONTENT (47%), ACRYLIC WATERPROOFING COATING

As a Bonding Primer

- For a bonding primer mix Dr. Fixit Pidicrete WP : Cement in the ratio 1:1 by volume
- Brush apply 1 continuous coat of the mix on the prepared concrete substrate
- Ensure to overlay the repair mortar when the bond coat is still tacky

As an additive for Repair Mortars & Renders

- A suitable mix ratio for patching repair mortar or render is as follows:
- Mix design - Portland Cement: 50 kg, Washed sand: 150 kg, Dr. Fixit Pidicrete WP: 5 kg & Water: 15-20 Lit

As an Additive for Floor Screeds & PCC

- A suitable mix ratio for patching repair mortar or render is as follows:
- Mix design - Portland Cement: 50 kg, Washed sand: 75kg, 6mm downsize aggregates: 75 kg, Dr. Fixit Pidicrete WP: 5 kg & Water: 15-20 Lit

As a coating for Reinforcing Steel priming

- Apply one coat of Dr. Fixit Pidicrete WP mixed cement slurry (1:1 by volume) to all exposed steel reinforcement and allow it to dry.
- A second coat application is also recommended. Allow it to dry. The surface should be thoroughly soaked with clean water prior to application of Dr. Fixit Pidicrete WP
- Apply Dr. Fixit Pidicrete WP with brush or rollers on the substrate and avoid ponding and remove any excess material. The repair or topping application should be carried out whilst the primer is still tacky.

Precautions & Limitations

- Recommended dosage to be followed to achieve desired results.
- When working in hot temperature conditions, extra water may be added to the repair mortar to compensate for the evaporation loss & make the mortar workable
- When using as a waterproofing coating, work on a saturated surface dry cementitious substrate

Technical Information

| Properties | Specification | Results |
|--|---------------------|--------------------|
| Appearance | | Milky white liquid |
| Adhesion strength to concrete, N/mm ² | BS 6310 Part 4:1984 | 38 |
| Pot life, mins | | 60 |
| Solid Content, % | | 47± 2 |
| Compressive strength, N/mm ² | BS 6310 Part 2:1983 | 10-13 at 7 days |
| Chloride content | | Nil |
| PH | | 7.7 |

Dr. Fixit Pidicrete WP

HEAVY DUTY, HIGH SOLID CONTENT (47%), ACRYLIC WATERPROOFING COATING

Coverage

- As a waterproofing coating: 30-35 sq.ft./ kg in 2 coats
- As a mortar modifier: 5 kg of Dr. Fixit Pidicrete WP per 50 kg of cement
- As a bonding agent: 45 - 50 sq.ft./ kg per coat

Packaging

1, 5 & 20 Kg

Shelf Life & Storage

- Shelf life is 12 months from the date of manufacturing in unopened condition.
- Store in cool & dry place, away from direct sunlight and at a temperature not more than 30°C.

Health & Safety Precautions

- Dr. Fixit Pidicrete WP is non-flammable.
- Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment during application.
- In case of contact with skin, rinse with plenty of clean water and then cleanse with soap water.
- In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice.

Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited
Construction Chemicals Division
Ramkrishna Mandir Road
Post Box No. 17411
Andheri (E) Mumbai 400059 INDIA
Tel +91-22-2835 7000 • Fax +91-22-2835 7008
website www.doctor-fixit.com • E-mail drfixit@pidilite.com
E-mail drfixitadvice@pidilite.com
Dr. Fixit Advice Centre (Toll Free No.) 1800-209-5504

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.