

Description

ShaliKote[®] LM is an elastomeric, liquid applied, emulsified asphalt membrane designed for waterproofing sunken floors, balconies and chajjas.

Characteristics - Physical

Appearance	Viscous brownish	Drying Condition,	40
	emulsion dries to	minutes / coat	(depending upon the
	black coating		climate condition)
Specific Gravity @ 30 °C	1.03 ± 0.01	Application Condition	Not to be used <5 ^o C or RH >85%**
Viscosity on Brookfield @ 25 °C, cps	2800 - 3000	Theoretical coverage, kg / m ² @ 1 mm DFT*	2.5
рН	Alkaline	Water Resistance	No Re-emulsification

* Depending upon surface condition.

If it is applied below 5 °C or relative humidity >85%, film formation time will be higher.

Characteristics – Technical

Properties	Standard	Result
Elongation after 7 days (1.50 mm film),%	ASTM D-412	200 - 250
Hardness, shore A (After 7 days)	ASTM D-2240	45 -50
Crack bridging, mm, maximum	ASTM C-826	0.5
Pull Off Adhesion, after 7 days, MPa	ASTM D-454	0.6

Application

- Water proofing of sunken, balconies and chajjas.
- Facade damp proofing.

Advantages

- Water based product, cleaner technology, non toxic.
- Easy to apply by brush and roller.
- Cold applied material.
- Excellent impermeability.
- Good flexibility and does not crack on aging.
- Seamless elastomeric membrane.
- Can be applied in damp surface

Application Methodology

Surface Preparation

• Ensure that surface is free from all loose gravel, dirt and foreign matter with highpressure wash. Before application surface should be totally dry, free from moisture, oil, grease, mill scale or rust.

> Application of Material

- Prime the surface with the mixture of **ShaliKote[®] LM** and water in 50:50 ratios. Slightly damp surface will help coating.
- Allow it to dry completely.
- Apply **ShaliKote[®] LM** by brush / roller on primed surface @ 1.0 kg / m² as first coat.

- Spread non-woven ShaliGeoText of 50 gsm polyester base mesh fiber cloth over the first coat of **ShaliKote**[®] **LM** when the surface is tacky with an overlap of 50 mm on both directions.
- Allow the first coat to dry with the reinforcement spread as above.
- Apply second coat of ShaliKote[®] LM @ 1.0 kg / m² or as required to get thickness of 1.2 1.5 mm.
- Conduct pond testing after 3 days of curing of second coat of ShaliKote® LM.
- For trafficable area, protect **ShaliKote**[®] **LM** with screed / tiles / china mosaic with a separation layer of ShaliGeoText of 120 -150 gsm. For screed finish, ShaliPolyFibre @ 600 gm / m³ and ShaliPlast LW+ / STP No 1 (Liquid) @ 200 ml / bag of cement may be used to improve the resistance to crack formation and impact resistance.
- For non-trafficable area, top coat with SuperSilverShield / ShaliCryl 215 for UV protection and aesthetics.
- Coverage shall depend on application and surface finish of substrate.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapor.
- Wear suitable protective clothing, gloves and eye protection
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash immediately with plenty of clean water and seek medical advice.
- If swallowed seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 kg and 200 kg pack.

Storage

Store in a cool dry place, under shed, away from heat.

Shelf Life

12 months in original unopened sealed condition.





2422016